

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
 Organization  
 International Bureau



(43) International Publication Date  
 19 February 2004 (19.02.2004)

PCT

(10) International Publication Number  
**WO 2004/014123 A1**

(51) International Patent Classification<sup>7</sup>: **A01G 13/02,**  
 C09K 17/52

(21) International Application Number:  
 PCT/FI2003/000600

(22) International Filing Date: 12 August 2003 (12.08.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
 0210262 13 August 2002 (13.08.2002) FR

(utility model), EE, ES, FI (utility model), FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK (utility model), SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicants (*for all designated States except US*):  
**AHLSTROM RESEARCH AND SERVICES [FR/FR];**  
 Z.I. de l'Abbaye Impasse Luis Champin, F-38780  
 Pont-Evêque (FR). **AHLSTROM CORPORATION**  
 [FI/FI]; Eteläesplanadi 14, FIN-00130 Helsinki (FI).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **GIRARD, Pierrick**  
 [FR/FR]; 29 Rue Claude Jusseaud, F-69110 Sainte Foy  
 Les Lyon (FR). **DUSSAUD, Joseph** [FR/FR]; 40 Montée  
 Charlemagne, F-38200 Vienne (FR). **VREVIN, Laurence**  
 [FR/FR]; 12 Rue Boson, F-38200 Vienne (FR). **PAPA,**  
**Fabrice** [FR/FR]; 11 Hameau de la Gère, F-38780 Vienne  
 (FR).

(74) Agent: **AHLSTROM KARHULA SERVICES LTD;** In-  
 tellectual Property Department, P. O. Box 18, FIN-48601  
 Karhula (FI).

(81) Designated States (*national*): AE, AG, AL, AM, AT (uti-  
 lity model), AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA,  
 CH, CN, CO, CR, CU, CZ (utility model), CZ, DE (uti-  
 lity model), DE, DK (utility model), DK, DM, DZ, EC, EE

**Declaration under Rule 4.17:**

— *as to the identity of the inventor (Rule 4.17(i)) for the fol-  
 lowing designations AE, AG, AL, AM, AT, AU, AZ, BA, BB,  
 BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK,  
 DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU,  
 ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT,  
 LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ,  
 OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY,  
 TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM,  
 ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ,  
 TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ,  
 MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY,  
 CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC,  
 NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG,  
 CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)*

**Published:**

— *with international search report*

*For two-letter codes and other abbreviations, refer to the "Guid-  
 ance Notes on Codes and Abbreviations" appearing at the begin-  
 ning of each regular issue of the PCT Gazette.*

(54) Title: BIODEGRADABLE FIBROUS SUPPORT FOR SOIL MULCHING

(57) Abstract: Biodegradable fibrous support for soil mulching, characterized in that it further contains biodegradable thermobond-  
 ing fibres distributed into the mass.



WO 2004/014123 A1

## BIODEGRADABLE FIBROUS SUPPORT FOR SOIL MULCHING

The invention relates to a biodegradable fibrous support for soil mulching, which can be used especially in the field of horticulture, market gardening, landscaping (tree nursery, green spaces).

In the rest of the description, the expression "fibrous support" denotes a support based on coniferous or deciduous unbleached or bleached plant fibres, or fibres of annual plants such as cotton, ramie, jute, flax, hemp etc., or synthetic fibres such as e.g. viscose, these fibres being biodegradable and they can be used by themselves or as a mixture, said support being furthermore able to comprise additives, in a manner that is not exhaustive, such as carbon black, hydrophobic resins (epichlorhydrin, polyamide etc.), fungicide, fungistatic and bactericidal agents, the mass of the support being between 40 g/m<sup>2</sup> and 200 g/m<sup>2</sup>, advantageously 150 g/m<sup>2</sup>.

The materials for mulching of the soil have to solve a certain number of the following objectives: prevent the weeds from growing shoots, maintain the structure of the soil, control the variations of the climate (moisture, temperature), assure a regular production both quantitatively and qualitatively, and make possible their mechanical application on the ground.

Several types of soil mulching materials are nowadays proposed, among which the plastic films and papers and nonwovens can be distinguished.

Firstly, black plastic sheeting is known, which has the advantage of being solid, despite its low weight per unit area, and thus being weather-resistant. However, this plastic sheeting has a certain number of drawbacks, especially that of not being biodegradable, its lifetime being in the order of 450 - 600 years. For obvious environmental reasons, plastic cannot be buried in the soil. Consequently, when the harvesting has been completed and the grower wishes to plough his land, he must completely remove the plastic. The cost of this operation is estimated to be 20% of the total cost of the mulching.

Moreover, since the plastic heats up very quickly when exposed to solar rays, the leaves of the plant close to the ground adhere and then burn having as consequences, firstly, the decrease of the productivity because of delayed growth and, secondly, they  
5 can only be removed with removal of this film. It is estimated that the removal of one ton of plastic entails the removal of one ton of plants and earth that have remained attached to the said plastic. Consequently, the plastic is virtually unrecyclable, the cost of washing it being unacceptably high for such an operation.

10 To solve the problem related to biodegradability, attempts have been made to manufacture films based on biodegradable materials, such as polymers of polylactic acid (PLA). In this sense, the document FR-A-2 733 520 describes association of a net or a "spunbund" of PLA with a film based on BAPE (biodegradable aliphatic polymer), i.e. a material from fossil resources (oil or gas) by heat sealing. However, this type of  
15 product has the inconvenience of being expensive to produce. Moreover, and above all, the fossil resources last for a limited period and, at least as far as oil is concerned, its reserve is estimated to last about forty years (source BP). Accordingly, the use of these materials for mulching of the soil is eventually compromised.

20 The document EP-A-637 641 describes, still concerning mulching, a non-woven composed of filaments produced entirely of a polymer or a polymer mixture derived from lactic acid. One of the main disadvantages of this kind of a product is its cost.

The mulching papers have inverse properties i.e. their degradability is fast, but on  
25 the other hand, their mechanical characteristics, especially their tearing strength, are low compared with plastics.

To solve this problem, the document FR-A-2 016 071 describes mulching papers treated with urea-formaldehyde resins. However, despite this treatment, the paper can  
30 break due to the effect of the watering phases, which expand the paper, and of the drying phases which retighten the paper.

The document WO 01/25536 of the Applicant describes a mulching paper comprising a resin based on epichlorhydrin, the paper being degraded by spraying an enzymatic solution capable of destroying both the resin and the cellulose. However, the described papers are adapted to short growing periods e.g. of the lettuce type. In particular, the mentioned paper based on deciduous fibres (20 %), coniferous fibres (50 %) and epichlorhydrin resin (3 %), sold by the Applicant under the trademark SEQUANA<sup>®</sup>, has a satisfactory strength during 3 - 4 months only, thus preventing its use for longer growing periods of e.g. 4 - 5 months with regard to melons, 9 months for the strawberries, 2 - 4 years in the field of tree nursery and green spaces.

10

The document JP2222421 describes a biodegradable mulching paper composed of a support based on plant fibres coated with an emulsion comprising as main constituent a copolymer of polyhydroxybutyrate acid (PHB) and polyhydroxyvalerianic acid (PHV) as a mixture with a natural polymer of starch and cellulose type and a synthetic polymer such as polylactic acid. No information is given regarding lifetime of this kind of a support. And once again we are confronted with the problem related to cost reasons.

15

20

In other words, the problem that the invention aims to solve is that of developing a mulching support based on plant fibres, which would be inexpensive, resistant during the relatively long-term growing, in practice in the order of 1 - 36 months and 100 % biodegradable within a time limit as short as possible after said growing has ended and at a low cost.

25

To do this, the invention proposes a biodegradable fibrous support for mulching of the soil, characterized in that it further contains biodegradable thermobonding fibres distributed in the mass.

30

In the rest of the description and in the claims, the expression "thermobonding fibres" denotes short fibres having a size of between 1 and 30 mm, preferably in the order of 5 mm, the average melting point of which is between 60°C and 180°C, these fibres being able to melt during the manufacturing process of the support so as to bind the fibres nearby and to strengthen the mechanical properties of the said support. In

practice, the fibres are chosen so that they melt at the temperature, at which the support is manufactured, which is about 100°C if the support is manufactured on a paper machine and about 170°C if the support is manufactured on a non-woven machine.

5       The thermobonding fibres of the invention may have a unique or double melting point on the assumption that the fibre is in the form of a so-called "bicomponent" fibre, corresponding to a fibre comprising two polymers having distinct physical and/or chemical characteristics, extruded from the same die for forming a single filament. In other words, the fibre in is the form of a core, having a first melting point surrounded by  
10       a sheath having a second lower melting point. This is e.g. the case with PLA-fibres sold by UNITIKA under the trademark TERRAMAC®, especially under the reference PL80, the core and sheath melting points of which are equal to 170°C and 130°C, respectively.

15       In an advantageous embodiment, the thermobonding fibres therefore consist exclusively of polylactic acid fibres such as e.g. the above-mentioned.

20       In other words, the invention consists in incorporating thermobonding fibres into the fibrous support, which allows to reinforce the mechanical strength of the support during the whole growing period, yet without delaying the degradation process of the plant fibres, which is faster than that of the material making up the thermobonding fibres.

25       In practice, the thermobonding fibres represent between 5 and 50% by weight, advantageously between 10 and 15% by weight of the support. For a concentration of less than 5%, there aren't enough fibres to reinforce efficiently the mechanical characteristics of the support. For a concentration more than 50%, the support is economically less interesting.

30       In a particular embodiment, to reinforce the fibrous support, said support is provided with a grid, which is either maintained on the whole or part of at least one face of the support, or incorporated into the whole or part of the mass of the support.

In the rest of the description and in the claims, the expression "grid" denotes a grid formed by a network of crossed non-woven threads comprising at least two webs of warp and weft threads, these warp and weft threads being interconnected at their crossings by a bonding agent creating a series of gluing points. This type of a grid and its manufacturing process are described more precisely e.g. in the document EP-A-1 111 114.

In practice, the grid is produced of biodegradable polymers chosen from the group comprising polylactic acid, polycaprolactone, viscose, modified viscose such as of the LYOCCELL or MODAL type, polyhydroxybutyrate and polyhydroxyalcanoate, by themselves or as a mixture. In an advantageous embodiment, the grid is produced exclusively of modified viscose threads and corresponds e.g. to the grid sold by CHAVANOZ INDUSTRIE under the reference 4032/71. According to another embodiment, the grid is produced solely from polylactic acid fibres such as those sold e.g. under the trademark TERRAMAC® by the company UNITIKA.

In practice, the grid has a weight of between 10 and 50 g/m<sup>2</sup>, advantageously in the order of 20 g/m<sup>2</sup>.

According to a first embodiment of the invention, the grid is maintained on the whole surface of the support, at least on one or both of the faces according to preference, the grid being able to be placed facing either the soil or the sky. In this case, the mulching will be more particularly adapted to long growing of several months.

In a more economical second embodiment, the grid is placed exclusively in the area of fixing points of the support in the soil, that is to say in the area of air/ground/substrate interface. The Applicant has in fact noticed that the micro organisms in the soil degraded the support and had an important effect on its strength at the fixing points, making it especially sensitive to the weather, especially to the wind. The fitting of the grid in the area of these fixing points, on one or both of the support faces, thus allows slowing down its biodegradation at the points that are sensitive, yet without affecting this process, which is slower, on the part which is not buried.

In practice, the grid is glued directly against the surface of the finished fibrous support by means of a biodegradable water-resistant glue chosen from the group comprising ethylene polyvinyl alcohol (EVOH) and polyvinyl alcohol (PVA), by themselves or as a mixture. In practice, the glue represents between 5 and 50 %, advantageously 15 %, by weight of the grid.

Moreover and according to another characteristic, the support may be subjected to a lime sludge/ micrite coating step before or after gluing of the grid.

10

In a third embodiment, the grid is not glued but directly integrated into the mass of the support during the manufacturing process of the latter. Here again, the grid may be arranged over the whole surface of the support or exclusively in the area of the fixing points of the support on the ground. In practice, the grid is unrolled directly on the fibrous support during formation on the wire of the paper or non-woven machine, the grid in the finished product thus being entangled to the surface of the support. Furthermore, with this technique, glue is no longer needed.

15

In any case, the fibrous support may contain a hydrophobic resin representing 0,5 – 15%, advantageously 6 – 8%, by weight of the support, chosen from the group comprising urea-formaldehyde resins, melamine-formaldehyde resins, polyamide-amine-epichlorhydrin resins, polyethyleneimine resins, starch derivatives, by themselves or as a mixture.

20

Depending on the colour of the fibres used, the support may further comprise carbon black representing 0,5 - 4% by weight of the support.

25

In an advantageous embodiment, the fibrous support of the invention can be advantageously coated with an aqueous solution comprising 5 – 50% by weight of biodegradable natural latex obtained from the rubber tree, the balance to 100 % consisting of water, stabilizing and preservative agents of latex. The synthesis molecules such as bactericides (such as e.g carbendazine, isothiazoline), fungicides or

30

fungistats (such as e.g. potassium sorbate) can also be incorporated into the coating solution, even if for regulation reasons, these substances are to be more and more avoided.

- 5        Among the stabilizers are especially denoted, but in a non limitative manner, the substances chosen from the group comprising the vegetable proteins such as especially casein, soya protein, the fillers such as talc, calcium carbonate, by themselves or as a mixture.
- 10       In the list of the preservatives of latex, i.e. the agents able to avoid the degradation of the latex by the micro-organisms, appear especially the substances chosen from the group comprising the animal proteins such as glycerine, but also the tennins, especially that of mimosa, the natural colouring agent indigo, chitosan, by themselves or as a mixture. For allowing the fixation of tannin on the fibrous support, the coating solution
- 15       contains metallic salts such as e.g. the aluminium sulphate  $Al_2(SO_4)_3$ .

In practice, the stabilizers represent from 1 to 50 % by weight of the coating solution. Also, the preservative agents represent from 1 to 30 % by weight of the coating solution.

20

According to another characteristic, the coating solution is coated in an amount of 10 to 200 g/m<sup>2</sup> as dry matter of latex, advantageously between 90 and 100 g/m<sup>2</sup>.

- 25       In practice, the latex used is obtained from Hevea Brasiliensis and it has a dry rubber concentration at least of 60%. A latex corresponding to this definition is, for example, the one sold under the trademark ALCANTEX<sup>®</sup> by the company SAFIC-ALCAN.

- 30       Instead of natural latex, the fibrous support of the invention can be advantageously coated with an aqueous solution comprising 5 – 50% by weight of biodegradable prevulcanized natural latex obtained from the rubber tree. Prevlcanized natural latex is, for example, sold under the trademark REVULTEX MR<sup>®</sup> by the company SAFIC-ALCAN.



The prevulcanized natural latex can be made biodegradable by utilizing sulphur-eating bacteria, like *sulfolobus acidocaldarius*, for example by adding the bacteria with the prevulcanized natural latex fibrous support. Besides being biodegradable, the prevulcanized natural latex is easier to handle, for example a lifetime is longer if required.

In a particular embodiment, the coating solution consists, by weight, of:

- from 5 to 50%, advantageously from 15 to 25%, biodegradable natural latex obtained from the rubber tree,
- from 1 to 20%, advantageously from 5 to 10%, vegetable proteins,
- from 0 to 20%, advantageously from 5 to 10%, talc,
- from 0,1 to 1%, advantageously 0,5%, biocide,
- the balance to 100 part consisting of water.

In an advantageous embodiment, the biocides represent from 1 to 20 % by weight of the solution and are composed of chitosan and/or indigo, and/or glycerine, and/or tannin, by themselves or as a mixture.

When the grid is glued against the surface of the support, the coating of the support by the solution can be carried out before or after the fixing of the grid. In any case, whether the grid is incorporated during the manufacturing process or glued, the coated material obtained can be subjected to a lime sludge/ micrite coating step, that is to say to dry creping.

The thermobonding fibres distributed in the mass of the support, possibly in the presence of a grid and/or a coating based on latex from the rubber tree allows to maintain the mechanical resistance of the support during the whole growing period, yet without affecting the actual degradation process of plant fibres making up the said support. However, this actual degradation process of the support is directly dependent on its composition. In other words, the problem is how to define support compositions according to the desired growing periods.

Consequently and in a first embodiment, before the incorporation of biodegradable thermobonding fibres, the support fibre composition denoted hereinafter "support 1" is as follows:

- 5       - from 40 to 100%, advantageously from 70 to 90%, by weight of coniferous unbleached or bleached kraft fibres,
- from 0 to 60%, advantageously from 10 to 30%, of deciduous unbleached or bleached kraft fibres,
- 10       - grammage: from 40 to 200 g/m<sup>2</sup>, advantageously 75 g/m<sup>2</sup>.

This type of fibrous composition will be especially suitable for short growing periods from about 1 to 6 months.

In a second embodiment, before the incorporation of the biodegradable thermobonding fibres, the fibre support composition denoted hereinafter "support 2" is as follows:

- 15       - from 80 to 100% by weight of annual plant fibres,
- from 0 to 20%, advantageously from 5 to 15%, by weight of coniferous unbleached or bleached kraft fibres.
- 20       - grammage: from 40 to 200 g/m<sup>2</sup>, advantageously 90 g/m<sup>2</sup>.

The fibres from annual plants can come from all types of annual plants rich in fibres, which can be used in paper mills and in the field of non-wovens e.g. of the cotton, ramie, jute, flax, hemp etc. type. In an advantageous embodiment, the fibrous composition

25       contains only fibres that come from annual plants.

This type of composition will be especially suitable for longer growing periods from about 6 to 18 months.

30       In a third embodiment, before the incorporation of the biodegradable thermobonding fibres, the fibre support composition denoted hereinafter "support 3" is as follows:

- from 20 to 100% by weight of coniferous bleached kraft fibres, advantageously from red cedar wood-oil,
- from 0 to 40%, advantageously 20 – 30%, by weight of fibres from annual plants,
- from 0 to 40%, advantageously from 20 to 30%, by weight of rayon or viscose fibres.
- grammage: from 40 to 200 g/m<sup>2</sup>, advantageously 100 g/m<sup>2</sup>.

In practice, the supports are manufactured on a nonwoven machine, and then bond by mechanical and/or hydraulic needling. The support can also be manufactured by a carding process and then bound by mechanical and/or hydraulic needling process.

In an advantageous embodiment of the support 3, the fibrous composition further contains a very small amount of bactericide carbon fibres, that is to say carbon fibres doped with silver salts, in the order of 0,5 – 2% by weight.

This type of composition will be especially suitable for longer growing periods from about 18 to 36 months.

The invention and the advantages which stem therefrom will become more apparent from the following illustrative examples.

#### Example 1

A support with the following composition, by dry weight, was prepared:

- 73% of fibre suspension comprising 100% by weight of coniferous unbleached or bleached kraft fibres
- 20% of PLA-fibres, the average length of which is 5mm, sold by UNITIKA under the reference PL80
- 3% of epichlorhydrin resin
- 4% of carbon black
- grammage: 75 g/m<sup>2</sup>

A sheet is formed on a paper machine from all constituents of the support. The support obtained this way is creped and then dried.

#### Example 2

5

The same procedure is repeated as for the support 1, with the exception that the fibre suspension contains 100% by weight of annual plant fibres (cotton, ramie, jute, flax, hemp). Grammage: 90 g/m<sup>2</sup>.

#### 10 Example 3

A support with the following composition, by dry weight, was produced:

- 73% of fibre suspension comprising:
  - 50% by weight of coniferous bleached kraft fibres, red cedar wood-oil
  - 15 - 25% by weight of annual plant fibres (cotton, ramie, jute, flax, hemp)
  - 25% by weight of rayon fibres
- 20% of PLA-fibres, the average length of which is 5 mm, sold by UNITIKA under the reference PL80
- 3% of epichlorhydrin resin
- 20 - 4% of carbon black
- grammage: 100 g/m<sup>2</sup>

A sheet is formed on a paper machine from all constituents of the support. The sheet to be formed is subjected to a hydraulic entanglement step known by the name  
25 JETLACE. Next, the support is dried and then dry-creped/ coated with micrite.

#### Example 4

After the final drying stage, a grid of modified viscose sold by CHAVANOZ  
30 INDUSTRIE under the reference 4032/71 is glued in each of the examples 1 – 3, the glue representing 15% by weight in relation to the weight of the grid.

Example 5

Right after the drying steps carried out in the examples 1 – 4, the support is coated with a solution consisting (by weight) of:

- 5     - 50% natural latex sold under the trademark ALCANTEX<sup>®</sup> by the company SAFIC-ALCAN
- 5% proteins,
- 10% talc,
- 1% biocide,
- 10    - 34% water.

Finally, the coated support obtained is dried.

**CLAIMS**

1. A biodegradable fibrous support for mulching of the soil, **characterized** in that it further contains biodegradable thermobonding fibres distributed in the mass.  
5
2. A support according to Claim 1, **characterized** in that the thermobonding fibres consist exclusively of polylactic fibres.
3. A support according to Claim 1, **characterized** in that the thermobonding fibres represent between 5 to 50% by weight, advantageously between 10 to 15% by weight of the support.  
10
4. A support according to Claim 1, **characterized** in that it is provided with a grid, which is either maintained on the whole or part of the at least one face of the support, or  
15 incorporated into the whole or part of the mass of the support, said grid being produced of biodegradable polymers chosen from the group comprising polylactic acid, polycaprolactone, viscose, modified viscose, polyhydroxybutyrate and polyhydroxyalcanoate, by themselves or as a mixture.
- 20 5. A support according to Claim 4, **characterized** in that the grid is made exclusively of modified viscose threads.
6. A support according to Claim 4, **characterized** in that the weight of the grid is between 10 and 50 g/m<sup>2</sup>, advantageously in the order of 20 g/m<sup>2</sup>.  
25
7. A support according to Claim 4, **characterized** in that the grid is positioned exclusively in the area of the fixing points of the support on the ground.
8. A support according to Claim 4, **characterized** in that the grid is glued directly on  
30 the surface of the fibrous support by means of a water-resistant biodegradable glue chosen from the group comprising ethylene polyvinyl alcohol (EVOH) and

polyvinyl alcohol (PVA), by themselves or as a mixture, the glue representing between 5 and 50%, advantageously 15 %, by weight of the grid.

5 9. A support according to Claim 4, **characterized** in that the grid is unrolled directly on the fibrous support during its manufacture.

10 10. A support according to Claim 1, **characterized** in that it contains a hydrophobic resin representing from 0,5 to 15% by weight of the support, chosen from the group comprising urea-formaldehyde resins, melamine-formaldehyde resins, polyamide-amine-epichlorhydrin resins, polyethyleneimine resins, starch derivatives, by themselves or as a mixture.

15 11. A support according to Claim 1, **characterized** in that it contains carbon black representing from 0,5 to 4% by weight of the support.

20 12. A support according to Claim 1, **characterized** in that it is coated with an aqueous solution comprising from 5 to 50% by weight of biodegradable natural latex obtained from the rubber tree, the balance to 100 % consisting of water, agents stabilizing and preserving the said latex.

25 13. A support according to Claim 1, **characterized** in that it is coated with an aqueous solution comprising from 5 to 50% by weight of biodegradable prevulcanized natural latex obtained from the rubber tree, the balance to 100 % consisting of water, agents stabilizing and preserving the said latex.

30 14. A support according to Claim 12 or 13, **characterized** in that the natural latex (therefore biodegradable) used is obtained from Hevea Brasiliensis and has a dry rubber concentration at least of 60%.

15. A support according to Claim 12 or 13, **characterized** in that the stabilizing agents are chosen from the group comprising the vegetable proteins such as especially casein, soya protein, the fillers such as talc, calcium carbonate, by themselves or as a mixture.

16. A support according to Claim 12 or 13, **characterized** in that the preservative agents are chosen from the group comprising the animal proteins such as glycerine, but also the tannins, especially that of mimosa, the natural colouring agent indigo, the chitosan, by themselves or as a mixture.

17. A support according to Claim 1, **characterized** in that the coating solution contains by weight of:

- from 5 to 50 % biodegradable natural latex obtained from the rubber tree,
- from 1 to 20 % proteins,
- from 0 to 20 % of talc,
- from 1 to 20 % of chitosan, and/or indigo, and/r glycerin, and/or tannins,
- the balance to 100 % consisting of water.

18. Support according to Claim 1, **characterized** in that, before the incorporation of the biodegradable thermobonding fibres, the fibre composition of the support is as follows:

- from 40 to 100% by weight of coniferous unbleached or bleached kraft fibres;
- from 0 to 60% by weight of deciduous unbleached or bleached kraft fibres.

19. Support according to Claim 1, **characterized** in that, before the incorporation of the biodegradable thermobonding fibres, the fibre composition of the support is as follows:

- from 80 to 100% by weight of annual plant fibres,
- from 0 to 20% by weight of coniferous unbleached or bleached kraft fibres.

20. Support according to Claim 1, **characterized** in that, before the incorporation of the biodegradable thermobonding fibres, the fibre composition of the support is as follows:

- from 20 to 100% by weight of coniferous bleached kraft fibres,
- from 0 to 40% by weight of annual plant fibres,
- from 0 to 40% by weight of rayon fibres.



## INTERNATIONAL SEARCH REPORT

International Application No.

PCT/FI/00600

A. CLASSIFICATION OF SUBJECT MATTER  
 IPC 7 A01G13/02 C09K17/52

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 A01G C09K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, WPI Data

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DATABASE EPODOC EUROPEAN PATENT OFFICE, THE HAGUE, NL; 30 April 1998 (1998-04-30), XP002241439 abstract & SI 9 600 317 A (JENKO ANTON MAG DIPL ING) 30 April 1998 (1998-04-30)	1, 12
A	FR 2 630 293 A (KAYSERSBERG SA) 27 October 1989 (1989-10-27) claims ----- -/--	1

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \* & \* document member of the same patent family

Date of the actual completion of the international search

6 November 2003

Date of mailing of the international search report

13/11/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
 NL - 2280 HV Rijswijk  
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
 Fax (+31-70) 340-3018

Authorized officer

Merckx, A

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/FI/00600

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DATABASE WPI Section Ch, Week 200019 Derwent Publications Ltd., London, GB; Class A23, AN 2000-218449 XP002241153 & JP 2000 045163 A (UNITIKA LTD) 15 February 2000 (2000-02-15) abstract	2
A	FR 2 813 888 A (NIEL JEAN FRANCOIS) 15 March 2002 (2002-03-15) the whole document	12, 14-17
A	FR 2 733 520 A (FIBERWEB SODOCA) 31 October 1996 (1996-10-31) cited in the application	

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/FR 93/00600

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
SI 9600317	A	30-04-1998	SI 9600317 A2	30-04-1998
FR 2630293	A	27-10-1989	FR 2630293 A1	27-10-1989
JP 2000045163	A	15-02-2000	NONE	
FR 2813888	A	15-03-2002	FR 2813888 A1	15-03-2002
FR 2733520	A	31-10-1996	FR 2733520 A1	31-10-1996
			AT 202941 T	15-07-2001
			CA 2175014 A1	27-10-1996
			DE 69613768 D1	16-08-2001
			DE 69613768 T2	08-05-2002
			EP 0747065 A1	11-12-1996
			US 5783504 A	21-07-1998